


ENTRY PLUGS POLYSTYRENE PS

Metric thread M 1.5 pitch CEI EN 60423

Ref. Light Grey	P	Ø A (mm)	C (mm)	Quantity
1253M12	M12X1,5	15	6	100
1253M16	M16X1,5	20	6	100
1253M20	M20X1,5	25	7	100
1253M25	M25X1,5	30	7	100
1253M32	M32X1,5	37	9	50
1253M40	M40X1,5	47	9	30
1253M50	M50X1,5	58	10	20
1253M63	M63X1,5	72	12	10

Add to Ref: N for Black

Pg thread DIN 40 430 - Dimensions DIN 46 320

Ref. Light Grey	P	Ø A (mm)	C (mm)	Quantity Box/Bag
1840	Pg 7	15	6	100
1841	Pg 9	19	6	500/100
1842	Pg11	22	7	100
1843	Pg13,5	25	7	100
1844	Pg16	27	7	100
1845	Pg21	33	9	50
1846	Pg29	44	9	100/50
1847	Pg36	55	10	20
1848	Pg42	62	10	10
1849	Pg48	69	12	10

Add to Ref: N for Black

Technical details:

PROTECTION :

IP 54 (EN 60529:1991 / CEI 70-1)

MATERIAL :

POLYSTYRENE PS

SELF-EXTINGUISHING CLASS :

CL. HB (UL 94)

TEMPERATURE RANGE :

-20°C ÷ +60°C (continuous)

RESISTANCE TO CHEMICAL:

See Annexe A

Resistance: A= Good, B= Fair, C= Poor

COLOUR:

RAL 7035 light grey, RAL 9005 black,

Cembre SpA

Via Serenissima, 9 - 25135 Brescia (Italy)

Tel.: +39 030 36921 - Fax: +39 030 3365766

Web: www.cembre.com - Email: info@cembre.com

Prepared by: Marketing dept.

Date: 19/07/2012

ENTRY PLUGS POLYSTYRENE PS
Annexe A:

Resistance: A= Good, B= Fair, C= Poor					
Resin in contact for 24 h					
No load applied			(PS)		
°C					
	Element	Conc.	23	50	75
INORGANIC ACIDS	Hydrochloric Acid	10%	B	B	
		35%	B	B	
	Nitric Acid	10%	B	B	
		35%	B	B	
	Sulfuric Acid	10%	A	A	
		35%	A	A	
	Hydrofluoric Acid	10%	B	B	
		50%	C	C	C
	Chromic Acid	10%	A	B	
		50%	B	B	
Aqua Regia	10%	B	C	C	
	50%				
ORGANIC ACIDS	Acetic Acid	10%	B	B	C
		50%	C	C	C
	Citric Acid	10%	A	B	
		50%			
	Formic Acid	10%	A	A	
		50%	A	A	
	Tartaric Acid	10%	A	B	
		50%			
	Acrylic Acid	10%			
		50%			
ALKALIES	Ammonia	10%	A	A	
		50%			
	Sodium Hydroxide	10%	A	B	
		50%	A		
	Potassium Hydroxide	10%	A	A	
		50%	A	A	
Ammonium Hydroxide	10%	A	B		
	50%				
ALCOHOLS	Butyl Alcohol (Butanol)	--	A	B	
	Methyl Alcohol (Methanol)	--	B	B	C
	Ethyl Alcohol (Ethanol)	85%	B	B	
	Cyclohexanol	--			
	Ethylene Glycol	--	A	A	A
	Isopropyl Alcohol (Isopropanol)		A	B	
	Glycolic Alcohol (Glycerol)	--			
KETONES	Acetone		C	C	C
	Cyclohexanone		C	C	C
	Formaldehyde	37%	C	C	C
	Methyl Ethyl Ketone		C	C	C
ESTERS	Ethyl Acetate		C	C	C
	Aliphatic esters				
ETHERS	Dioxane		C	C	C
	Ethylene Oxide Ossido di etilene		C	C	C

Cembre SpA

Via Serenissima, 9 - 25135 Brescia (Italy)

Tel.: +39 030 36921 - Fax: +39 030 3365766

Web: www.cembre.com - Email: info@cembre.com

ENTRY PLUGS POLYSTYRENE PS
Annexe A:

HALOGENATED ORGANIC COMPOSITES	Chloroform		C	C	C
	Methylene Chloride		C	C	C
	Perchloroethylene		C	C	C
	Carbon Tetrachloride (wet)		C	C	C
	Trichloroethylene		C	C	C
HYDROCARBONS	Benzene		C	C	C
	Gasoline (pure)		C	C	C
	Cyclohexane		C	C	C
	Heptane		C	C	C
	Brake Fluids		C	C	C
	Skydrol				
	Diesel Fuel		B	B	
	Kerosene		B	C	C
	Methane (gas)				
	Mineral Oil		A	A	
	Toluene		C	C	C
Xylene		C	C	C	
INORGANIC CHEMICALS	Nitrogen				
	Sodium Bicarbonate		A	A	
	Bromine	10%	C	C	C
	Chlorine (wet)		C	C	C
	Sodium Chloride	10%	A	B	
	Fluorine				
	Iodine (solution)		B	B	
	Sodium Hypochlorite		A	B	
	Oxygen (low pressure)				
	Ozone	<5 ppm	A		
	Sodium (hot)		A		
	Copper Sulfate	10%	A	B	
	Sulfur		A	A	
MISCELLANEUS	Sea Water		A	A	
	Hydrogen Dioxide (Peroxide)	30%	A	B	
	Distilled Water		A	A	
	Aniline		C	C	C
	Phenol (conc.)		B		

Cembre SpA

Via Serenissima, 9 - 25135 Brescia (Italy)

Tel.: +39 030 36921 - Fax: +39 030 3365766

Web: www.cembre.com - Email: info@cembre.com